



ANUPAM COLOURS & CHEMICALS INDUSTRIES

Head Office: 101-102, Kaveri Complex, Jagannath Mandir Road, Sakinaka Junction, Mumbai - 400 072

Phone: :+91-22-2850 6586, 2850 6532 Fax:+91-22-2852 5954

Website: www.anupamcoloursacci.com E-mail: info@anupamcoloursacci.com

ANCOR BARIUM CHROMATE B-91

ANCOR Barium Chromate B-91 is a pale yellow pigment. It liberates ions which are responsible for its anti-corrosive properties. This pigment is used in the manufacture of Primers for metals.

TECHNICAL DATA

Colour Index No.	77103
Colour Index Pigment No.	Y-31
Oil Absorption	8-20
Specific Gravity	4.0-4.5
Bulk Density g/cc	1.10
BLEEDING IN (1-Poor 5-Excellent)	
Water	5
5% Caustic Soda	4
5% Hydrochloric Acid	1
Linseed Oil	5
Ethanol	5
Ethyl Acetate	5
Xylene	5
n-Butanol	5
Methyl Ethyl Ketone	5
Mineral Turpentine	5
Cellosolve	5
Diocyl Phthalate	5
RESISTANCE TO HEAT	
120°C / 30 min.	SB
150°C / 20 min.	SB
180°C / 10 min.	SB
210°C / 10 min.	SB
RESISTANCE TO LIGHT	
Full Tone	8
APPLICATIONS	
Anti-Corrosive Primers	*

LEGEND

COLOUR	BLEEDING	HEAT STABILITY	LIGHTFASTNESS	APPLICATIONS	E-EXCELLENT
Y- YELLOW	SCALE (1-5)	SB: STABLE	SCALE (1-8)	*RECOMMENDED/ MAY BE USED	VG-VERY GOOD
R-RED	5: NO BLEED	USB: UNSTABLE	1- POOR		G-GOOD
W-WHITE	1: CONSIDERABLE BLED		8- EXCELLENT		F - FAIR P - POOR