



ANUPAM COLOURS & CHEMICALS INDUSTRIES

Head Office: 101-102, Kaveri Complex, Jagannath Mandir Road, Sakinaka Junction, Mumbai - 400 072

Phone: :+91-22-2850 6586, 2850 6532 Fax: +91-22-2852 5954

Website: www.anupamcoloursacci.com E-mail: info@anupamcoloursacci.com

ANUCHROME "MIDDLE CHROME" M-16

ANUCHROME M-16 is a monoclinic lead chromate pigment and is a raw material for the Paint Industry. This is an economical grade in Middle Chromes product range. This pigment is a stabilized one and it generally offers good fastness to light and weather. This pigment has fair dispersion characteristics.

TECHNICAL DATA

Colour Index No.	77603
Colour Index Pigment No.	Y-34
Oil Absorption	15-20
Specific Gravity	5.1-6.0
Bulk Density g/cc	1.05
BLEEDING IN	
Water	5
5% Caustic Soda	3
5% Hydrochloric Acid	3
Linseed Oil	5
Ethanol	5
Ethyl Acetate	5
Xylene	5
n-Butanol	5
Methyl Ethyl Ketone	5
Mineral Turpentine	5
Cellosolve	5
Diocyl Phthalate	5
RESISTANCE TO HEAT	
120°C / 30 min.	SB
150°C / 20 min.	SB
180°C / 10 min.	USB
210°C / 10 min.	USB
RESISTANCE TO LIGHT	
Full Tone	5
Tint Tone (1:10)	6
RESISTANCE TO	
Acid	G
Alkali	P
APPLICATIONS	
Paints	*
Printing Inks	*
Rubber	
Leather Pastes	*
Linoleum	*
PVC Leather Cloth	*
Paper Coating	*
Chalk / Crayons	
Plastics	*

LEGEND

COLOUR	BLEEDING	HEAT STABILITY	LIGHTFASTNESS	APPLICATIONS	E – EXCELLENT
Y – YELLOW	SCALE (1-5)	SB : STABLE	SCALE (1-8)	* :RECOMMENDED/ MAYBE USED	VG – VERY GOOD
R – RED	5:NO BLEED	USB : UNSTABLE	1 – POOR		G – GOOD
W – WHITE	1:CONSIDERABLE BLEED		8 – EXCELLENT		F – FAIR
					P – POOR